

High performing flexible homogeneous multipurpose flooring, durable with EASYCARETM surface treatment

MIPOLAM® 180 is a durable, high performing flexible homogeneous multipurpose flooring recommended for hospitals, schools, offices, supermarkets and institutional buildings. It is an ease to maintain, hardwearing floorcovering with an attractive and modern design. It benefits from EASYCARE™ surface treatment with good resistance to chemicals and to scuffing, and high resistance to scratches and staining. Easy to clean. No wax for life!





Key Features

- Excellent abrasion resistance
- Available in 2 m sheet
- Flexible flooring, easy to install & weld
- Matt finish surface: enhanced design & colour
- Homogeneous vinyl flooring suitable for medium to heavy duty traffic areas

Color number: 30

Sheet size: 200 cm x 20 lm

■ I Thickness: 2.0 / 2.5*

MIPOLAM® 180 features bacteriostatic and fungistatic treatment. The flooring complies with the EN 649 (34 - 43) and has a Group P wear rating. It is suitable for heavy traffic areas.

Colorline









2001



2005















2021 2008








EASYCARE™ surface treatment with good resistance to chemicals and to tscuffing, and high resistance to scratches and staining. Easy to clean. No wax for life!



Decorlux

EASYCARE™ surface treatment with good resistance to chemicals and to tscuffing, and high resistance to scratches and staining. Easy to clean. No wax for life!





INSTALLATION

Installation should be carried out in accordance with local standards. Subfloor should be smooth, hard, clean and dry prior to laying. Where applicable, the subfloor must incorporate an effective Damp Proof Membrane. The material must be allowed to acclimatize 24 hours before installation in a room temperature of between 18-24°C. All seams must be hot welded using Gerflor® matching welding rod.

MAINTENANCE

No emulsion dressing is required. Maintenance should be carried out regularly to retain in the appearance and durability of the floor. The floorcovering should be maintained with regular sweeping and damp mopping using a neutral cleanser. More intense cleaning should be carried out using a fine spray cleaning pad under a floor machine, or for larger areas combined machine cleaning.

Technical Specification

| DESCRIPTION | | | | |
|-------------------------|--------------------|---------|----------|------|
| Total thickness | ISO 24346 (EN 428) | mm | 2 | 2.5* |
| Weight | ISO 23997 (EN 430) | g/m² | 3150 | 3950 |
| Width / Length of sheet | ISO 24341 (EN 426) | cm / lm | 200 / 20 | |

| CLASSIFICATION | | | |
|------------------------------|--------------------|-------|-------------------|
| Norm / Product specification | - | - | ISO 10581(EN 649) |
| European classification | ISO 10874 (EN 685) | class | 34 - 43 |
| Fire rating | EN 13 501-1 | class | Bfl-s1 |
| Static electrical propensity | EN 1815 | KV | <2 |
| Electrical resistance | EN 1081 | Ω | 109-1010 |
| Slip resistance dry | EN 13893 | - | ≥0.3 |
| Slip resistance wet | DIN 51130 | class | R9 |

| PERFORMANCES | | | |
|---|----------------------|-----------------|------------------------|
| Wear resistance | EN 660.2 | mm ³ | ≤4.0 |
| Wear group | EN 649 | group | M |
| Type binder content | ISO 10581 | type | II |
| Dimensional stability | ISO 23999 (EN 434) | % | ≤ 0.4 |
| Residual indentation | ISO 24343-1 (EN 433) | mm | ≈0.04 |
| Castor chair test | ISO 4918 (EN 425) | | OK |
| Thermal conductivity | ISO 10456 (EN 12524) | W/(m.K) | ≈0.25 |
| Colour fastness | ISO 105 - B02 | degree | ≥ 6 |
| Chemical products resistance | ISO 26987 (EN 423) | - | OK |
| Anti-bacterial and fungicidal treatment | - | - | OK |
| Surface treatment | - | - | EASYCARE TM |
| Color number | - | - | 30 |

| ENVIRONMENT / INDOOR AIR QUALITY | | | |
|----------------------------------|---------------|-------|-------------|
| TVOC after 28 days | ISO 16000 - 6 | μg/m³ | <10 |
| Certification | - | - | Floorscore® |

| CE MARKING | | | | | |
|------------|----------|---|---|--------------|---------------------|
| C€ | EN 14041 | - | B | °97.57 DS | B _{ff} -s1 |

^{*} Special order, minimum quantities needed

